



Accura[®] 25

PP Class

Flexible plastic to simulate and replace CNC-machined white polypropylene articles.

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	U.S.
Tensile Strength (MPa PSI)	ASTM D 638	38	5540-5570
Tensile Modulus (MPa KSI)	ASTM D 638	1590-1660	230-240
Elongation at Break (%)	ASTM D 638	13-20	13-20
Flexural Strength (MPa PSI)	ASTM D 790	55-58	7960-8410
Flexural Modulus (MPa KSI)	ASTM D 790	1380-1660	200-240
Impact Strength (J/m Ft-lbs/in)	ASTM D 256	19-24	0.4
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	58-63 °C 51-55 °C	136-145 °F 124-131 °F
Coefficient of Thermal Expansion (CTE)	ASTM E 831-93 TMA (T<Tg, 0-20 °C) TMA (T<Tg, 75-140 °C)	107 x 10 ⁻⁶ 151 x 10 ⁻⁶	59.4 83.9
Glass Transition (Tg)	DMA, E''	72-74	162-165
Hardness, Shore D		80	80

Features

- Flexible
- Snap fit assemblies
- Master patterns for vacuum casting
- Durable functional prototypes

Liquid Material

MEASUREMENT	CONDITION	VALUE
Viscosity	@ 30 °C (86 °F)	230 cps
Penetration Depth (Dp)		4.2 mils
Critical Exposure (Ec)		10.5 mJ/cm ²
Color		White
Solid Density	@ 25 °C (77 °F)	1.19 g/cm ³ at 25 °C
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm ³ at 25 °C



www.3dsystems.com

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2020 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. 3D Systems, the 3D Systems logo, and Accura are registered trademarks of 3D Systems, Inc.